

# Procedures to remove penetrated oil stains engine oil, grease on marble, granite & all other type of stones

Mix SCL-OE2 chemical with SCL PPP Poultice Powder.  
Application procedures as follow:

1. Mix SCL-OE2 with SCL-PPP Poultice Powder into a paste. Used the plastic spatula to apply the paste on the stain area.  
只需將糊狀敷貼於污漬表面。



2. Cover the paste with clear plastic sheet and tape down the edges with a low adhesive tape.  
用一張透明塑料品包裝紙將敷劑覆蓋起來。用低粘性的膠紙固定住塑料紙將勿讓糊狀蒸發太快。靜置48小時。



3. Removed the plastic sheet after 48 hours if the poultice is still wet. Do not remove the poultice when it is semi-dry in this condition. Once removed for viewing, re-application of fresh poultice is required.

48小時后, 如糊狀未乾, 把塑料紙除掉, 留糊狀勿動24小時。如糊狀未乾時, 心急要看除污效果, 把糊狀刮開再覆蓋, 糊狀就會失去效果。



4. Leave the poultice to react for another 24 hours. Removed the poultice when it is thoroughly dry and hardened in this condition. Dispose the poultice in a plastic bag. 糊狀完全乾和硬化才能清理。把除污糊狀裝進塑料袋再處理。



# SCL OE2 removed ....

penetrated cooking oil, engine oil, candle wax, etc...



## Step 3. Apply the poultrice.

Carefully apply the poultrice to the stained area. Not too thin, generally about 1/4 inch thick is sufficient for most stains.

## Step 4. Cover the poultrice.

Cover the poultrice with a clear thin transparent plastic sheet or a plastic food wrap. Tape the poultrice with a low adhesive paper masking tape.

## Step 5. Remove the poultrice.

After the poultrice is thoroughly dry and harden approximate 1-2 days, sweep it off or scrape it off with a spatula. Dispose them in a plastic bag. Remove the paste only if the paste is thoroughly dry. Do not remove the paste unnecessarily for viewing.

If the stain has lightened, you possibly required a second attempt.

Clean the residues of the poultrice with SCL-Stoneclean or SCL-Stonemist.

**Important Note:** It is important that the paste must be thoroughly dry before it is removed.

## Applicable on the type of Stones:

Polished & rough texture surface marble, limestone, granite, slate, Terra-Cotta, homogeneous tiles and all types of natural stone.

## Benefit:

Shine remains on polished surface marble, granite and limestone, etc.

## SCL-OE2 Available Sizes:

1-litre & 25-litres

## SCL-PPP Poultrice Powder Available Sizes:

1-kg & 10kg

## One sq.ft required:

500ml of SCL-OE2 mixed with 200 grams of SCL-PPP Poultrice Powder

## Poultrice Procedures:

### **Step 1. Remove topical coating, (if any).**

If a thin film of coating is noted, removed with SCL-XY stripper before poultricing. Otherwise, you will be poultricing on the wax coating.

### **Step 2. Prepare the poultrice.**

Mix SCL-PPP Powder with SCL-OE(2) solution into a thick paste about the consistency of creamy peanut butter.



S  
C  
L

O  
E  
2