



TECHNICAL BULLETIN

Description/Features

SCL-Epoxy Sealer #800 is a Two-Components Sealer. It has a higher viscosity than Epoxy Sealer #300, thus it is ideal to fill bigger cracks and open veins and help to reduce rejection rate of undesirable stones.

Applicable on the type of stones:

All types of marble and granite

Instructions for use

1. The stone surface has to be dry.
2. Mix 100 grams of Component A to 50 grams of Component B. Strictly followed this mixing ratio, the sealer will cure & dry within 36 hours.
3. Once both part A and B are mixed together in a tub, stirred them well and apply the sealer immediately on to the stone surface.
4. Use a thin metal or acrylic plate to spread the sealer onto the stone surface in a thin layer. 20 minutes later, you could apply another thin layer 2nd coat of sealer to assure all holes are properly filled.
5. Mix a small portion at a time so to allow enough time to spread the sealer evenly onto the surface before the balance sealer gel-up.
6. Wait for the sealer to cure and harden before polishing. The sealer will harden after 6 hours at room temperature (25°C)

Available sizes:

Component A: 900 ml / 3.3 litres

Component B: 450 ml / 1.7 litres

Other sizes: Upon request

Approximate coverage for one set

900ml of Component A & 450ml of Component B covers approximate 250sq.ft to 350 sq.ft.

Benefits of SCL EPOXY SEALER

- ✓ Reduce visibilities of cracks, holes, open veins and reduce rejection rate of undesirable stones.



- ✓ Ideal to use as an adhesive to join 2 piece of stones together. Can also use to bond [Pebbles stone](#) together.



Note: Close the cap tight when the product is not in use.

Purchasers are required to test the suitability of the product for their intended use. mcare Lab Pte Ltd makes no warranty, expressed or implied on the products and the effects. mcare Lab Pte Ltd shall not responsible for any risks or liabilities, direct, indirect or consequential arising out of the used or the inability to use the product.